

Resolution 61-6

SPECIFICATIONS FOR SIDEWALK CONSTRUCTION, RECONSTRUCTION AND REPAIR.

Re. Ordinance #1118 - Section 2.

1. All sidewalks shall be constructed of Portland Cement concrete containing not less than 5 sacks of cement per cubic yard of concrete. All concrete shall be thoroughly mixed and shall be placed not later than 1 hour after all ingredients are placed in mixer.
2. All sidewalks shall be a minimum of 4 feet in width and all repaired or reconstructed sidewalks shall conform to existing widths.
3. All sidewalks shall be a minimum of $3\frac{1}{2}$ " in thickness, except at driveway entrances where the thickness shall be increased to 5" minimum, and reinforcing steel or welded wire mesh equivalent to 6" x 6" No. 10 x 10 shall be installed within the sidewalk at all driveway crossings.
4. Where possible, all sidewalks shall slope toward the street at the rate of $\frac{1}{4}$ " per foot of width.
5. $\frac{1}{2}$ " minimum expansion joints shall be installed at intervals not to exceed 30 feet. Expansion joint material shall be that specifically produced for this purpose. In lieu of expansion joints as specified, contraction joints may be installed by sawing at 30' minimum intervals. The annular space left by the saw cut shall be filled with an approved mastic.
6. Forms and subgrade shall be thoroughly dampened before pouring. All sidewalks shall be placed and maintained true to line and grade, and all new concrete shall be thoroughly tamped into place. The surface of all concrete shall be left equivalent to that texture obtained through use of a wood float. All edges shall be rounded.